

**AMENDMENTS TO OPSS 1010 (MAR 93) –  
MATERIAL SPECIFICATION FOR AGGREGATES – GRANULAR A, B, M, AND  
SELECT SUBGRADE MATERIAL <sup>1</sup>**

**OPSS 1010.05** is amended by the addition of the following:

**OPSS 1010.05.05** 19mm Crusher Run Limestone

19mm Crusher Run Limestone shall meet the physical requirements for Granular ‘A’ as shown in Table 1, and shall meet the following gradation:

<b>MTO Sieve Designation</b>	<b>Percentage Passing by Mass</b>
19 mm	100
16 mm	75-100
13.2 mm	65-90
9.5 mm	--
4.75 mm	35-55
1.18 mm	15-45
300 µm	5-22
150 µm	--
75 µm	0-8

**OPSS 1010.05** is amended by the addition of the following:

**OPSS 1010.07.02** 19 mm Crusher Run Limestone

19 mm Crusher Run Limestone shall be produced by crushing limestone.

**1. All references to OPS specifications that have been amended (as noted in LIST T3) are superseded by references to the replacement City of Toronto specifications (as given in LIST T3).**