

**AMENDMENTS TO OPSS 1860 (MAR 98) –
 MATERIAL SPECIFICATION FOR GEOTEXTILES ¹**

OPSS 1860.07.02.02 is superseded by:

All geotextiles shall conform to Table 1.

TABLE 1

Roll Properties	Requirements		Test Methods
	Non-Woven	Woven	
Minimum Grab Tensile (N)	450	556	CAN/CGSB-148.1 No. 7.3
Minimum Mullen Burst (MPa)	1.40	1.72	CAN/CGSB-4.2 No. 11.1
Minimum Tear (N)	210	200	CAN/CGSB-4.2 No. 12.2
Filtration Opening Size (µm)	50 to 150	300	CAN/CGSB-148.1 No. 10.2
Minimum Permeability (K)	0.20	0.10	CAN/CGSB-4.2 No. 11.1
Elongation % at Break	70 to 100	15	CAN/CGSB-148.1 No. 7.3

1. All references to OPS specifications that have been amended (as noted in LIST T3) are superseded by references to the replacement City of Toronto specifications (as given in LIST T3).