

**AMENDMENTS TO OPSS 929 (MAY 94) –
CONSTRUCTION SPECIFICATION FOR ABRASIVE BLAST CLEANING –
CONCRETE CONSTRUCTION ¹**

OPSS 929.03 The definition for abrasive is amended by the addition of the following:

Abrasives for blast cleaning shall be low free silica.

OPSS 929.07.04.01 is amended by the addition of the following:

Abrasive blast cleaning shall be carried out not more than 48 hours before the placement of new concrete.

OPSS 929.07.05 is amended by deleting the third and fourth paragraph and the addition of the following:

Placement of new concrete shall be done within 48 hours of abrasive blast cleaning of the reinforcing steel or the reinforcing steel shall be reblasted.

OPSS 929.09.02 is amended by the addition of the following subsection:

929.09.02.02 Abrasive Blast Cleaning

Abrasive Blast Cleaning of concrete surfaces and of reinforcing steel for concrete repair items will not be measured for payment unless otherwise indicated in the specifications.

OPSS 929.10 is amended by the addition of the following subsection:

929.10.02 Abrasive Blast Cleaning

Where no payment item is indicated, payment is deemed to be included in the appropriate tender item for concrete removal.

1. All references to OPS specifications that have been amended (as noted in LIST T1) are superseded by references to the replacement City of Toronto specifications (as given in LIST T1).